

ABSTRACT OF THE DISCLOSURE

Process Aid for Melt Processable Polymers

- 5 Extrusion processability of non-fluorinated melt-processable polymers is improved by introducing a fluoropolymer process aid by means whereby the weight average particle size of the fluoropolymer is greater than 2 microns as it reaches the extruder die entrance.